



Re-Sealing concrete Surfaces

Using StaSeal™ Premium Sealer

SURFACE PREPARATION

Do not acid etch previously sealed surfaces. Surface should be clean and free of dust, grease, oil, flaking sealer and other contamination.

For removal of grease and oil stains wet area with hot water then apply Cleanall scrub with a broom on and around area. Allow to sit 5 minutes then pressure wash.

For removal of moss or fungus dilute bleach 1 to 10 parts water in a watering can, apply over concrete and allow to sit for a minimum of 2 hours, then high pressure wash off completely. Repeat if necessary.

Prior to sealing it's advisable that a small area be tested for compatibility. Apply Solulene™ liberally and broom in vigorously, then apply StaSeal™ Premium and leave to weather for a minimum of 7 days.

If the Sealer™ on the test area fails, (delamination, flaking, cracking or surface remaining soft or tacky) the old sealer should be stripped with Sealer Strippa and resealed following the directions of unsealed surfaces.

If the test area is successful then apply Solulene™ liberally with a broom and work into the surface then proceed with the sealing application.

SEALER APPLICATION

First coat dilute equal parts of StaSeal™ Premium with Solulene™

Second Coat apply StaSeal™ Premium undiluted after minimum of 24 hours

Smooth finish surfaces the addition of 300 grams of Anti Slip per 20 lts StaSeal™ Premium in the final coat will reduce slipping and improve pedestrian safety. Stir frequently to ensure even coverage.

WARNING

Sealing steep surfaces is not recommended, can be very slippery in wet or dry conditions. **Sealing in warm weather** the addition of 2 lts Solulene™ in the final coat will help reduce blistering. **Sealing** early in the morning or late in the day is not recommended, due to early morning dew and night condensation. Sealer effected by moisture will lose gloss, adhesion properties and could have a white blooming appearance.

CURING

Full curing is not achieved for up to 7 days at ambient temperature 15 to 28 °C Avoid parking vehicles for up to 7 days. Allow foot traffic next day.

COVERAGE

Approximately 5 square metres per litre depending on porosity of concrete.

EQUIPMENT

Airless Spray Unit / Sealer Broom / Lambswool Applicator / Dacron Roller
Cleaning of equipment use Solulene™

Important Note

The information given is based on many years experience and is correct to the best of our knowledge. However, as the use of our product, surface conditions, weather and a number of other factors are completely beyond our control, we can only be responsible for the quality of our product at the time of dispatch. For further information contact the supplier. As this information is of a general nature the Supplier or Manufacturer cannot assume any responsibility for an individual case